

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 August 2001 (09.08.2001)

PCT

(10) International Publication Number
WO 01/56920 A2


- (51) International Patent Classification⁷: **B81B 7/00**
- (21) International Application Number: **PCT/US01/03210**
- (22) International Filing Date: 31 January 2001 (31.01.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/495,786 1 February 2000 (01.02.2000) US
- (71) Applicant: **MOTOROLA, INC.** [US/US]; 1303 East Algonquin Road, Schaumburg, IL 60196 (US).
- (74) Agents: **INGRASSIA, Vincent, B.** et al.; P.O. Box 10219, Scottsdale, AZ 85271-0219 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventors: **HUANG, Jenn-Hwa**; 1426 West Tara Drive, Gilbert, AZ 85233 (US). **COFFMAN, Samuel, L.**; 11603 North 86th, Scottsdale, AZ 85260 (US). **SUN, Xi-Quing**; 100 West Nopal Place, #236, Chandler, AZ 85225 (US). **XU, Ji-Hai**; 1232 South Buchanan Street, Gilbert, AZ 85233 (US). **PARSEY, John, Michael, Jr.**; 1321 East Desert Flower Lane, Phoenix, AZ 85048 (US).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: MICRO-ELECTROMECHANICAL SYSTEM DEVICE



(57) Abstract: A Micro-Electromechanical Systems (MEMS) device (100) having conductively filled vias (141). A MEMS component (124) is formed on a substrate (110). The substrate has conductively filled vias (140) extending therethrough. The MEMS component (124) is electrically coupled to the conductively filled vias (140). The MEMS component (124) is covered by a protective cap (150). An electrical interconnect (130) is formed on a bottom surface of the substrate (110) for transmission of electrical signals to the MEMS component (124), rather than using wirebonds.

WO 01/56920 A2

MICRO-ELECTROMECHANICAL SYSTEM DEVICE

Field of the Invention

5

The present invention relates, in general, to Micro-Electromechanical System (MEMS) devices and, more particularly, to manufacturing MEMS devices.

10

Background of the Invention

FIG. 1 illustrates a MEMS device 10 manufactured in accordance with a prior art technique referred to as a glass paste wafer capping technique. In this technique, a plurality of MEMS devices 11 (one shown) are manufactured on a device wafer 12 such as a silicon wafer. Independently, a screen print of glass paste is deposited on a second wafer 13, which is commonly referred to as a cap wafer. The glass paste is cured to form spacers 14, which are then aligned and bonded to device wafer 12. The two wafer combination is then diced by sawing into individual devices. A critical limitation of this technique is that the temperature needed to bond the glass spacers to the device wafer ranges from approximately 400 to 500 degrees Celsius (°C). Temperatures this high can easily damage the MEMS device. Another limitation of this technique is that it is relatively complicated due to the use of screen printing and wafer bonding procedures. Complicated processes are typically less cost efficient because of the added complexity and the lower yield of operational devices.

FIG. 2 illustrates a MEMS device 20 manufactured in accordance with a prior art technique referred to as

a cap/cavity technique. In this technique, a plurality of MEMS devices 21 (one shown) are fabricated on a device substrate 22, which is then diced into individual or singulated device components. Each individual MEMS component is subsequently attached to a packaging substrate 23. Packaging substrate 23 is typically ceramic in composition to prevent Radio Frequency (RF) losses that are inherent with substrates such as silicon. MEMS device terminals 26 are then coupled to package leads 27 via wirebonds 24. Then, the MEMS device is hermetically encapsulated with a ceramic cap 28.

One limitation of this technique is that each MEMS device is individually handled and bonded to packaging substrate 23. If the sacrificial protective layer separating the upper and lower control electrodes during fabrication is removed prior to handling, the MEMS device becomes extremely fragile and subject to damage during handling and bonding. If the sacrificial protective layer is not removed prior to handling and bonding, the processing becomes much more complicated due to substrate interaction when the sacrificial protective layer is later removed. In either case, the effective yield of the manufacturing process is adversely impacted. Another limitation of the cap/cavity approach is that the upper surface of packaging substrate 23 has many topographic variations which may prevent the creation of a hermetic seal between it and cap 28.

A limitation common to both the glass paste wafer capping technique and the cap/cavity technique is the requirement for wirebonding the MEMS device to external leads. An intrinsic limitation of wirebonding is the parasitic inductance inherent in the wirebond. This

parasitic inductance degrades the RF performance of MEMS devices.

Therefore, a need exists to provide a more reliable, cost effective, and robust MEMS device and
5 method of manufacture that overcomes the deficiencies of the prior techniques.

Brief Description of the Drawings

10 FIG. 1 illustrates a MEMS device manufactured in accordance with a prior art technique referred to as a glass paste wafer capping technique;

FIG. 2 illustrates a MEMS device manufactured in accordance with a prior art technique referred to as a
15 cap/cavity technique;

FIG. 3 is a cross-sectional side view of a MEMS device at an initial stage of manufacture;

FIG. 4 is a cross-sectional side view of the MEMS device of FIG. 3 at a later stage of manufacture;

20 FIG. 5 is a cross-sectional side view of the MEMS device of FIG. 4 at a later stage of manufacture; and

FIG. 6 is a top view of the MEMS device of FIGS. 3-5.

25 For simplicity and clarity of illustration, elements in the drawings are not necessarily drawn to scale, and the same reference numerals in different figures denote the same elements.

30

Detailed Description of the Drawings

FIG. 3 illustrates an initial stage in the manufacture of a MEMS device 100. What is shown in

FIG. 3 is a cross-sectional side view of a packaging substrate 110 having surfaces 111 and 112 and a plurality of vias 141 selectively formed therein.

Conventional photolithographic methods may be employed
5 to form vias 141. It should be understood that the techniques for forming vias 141 is not a limitation of the present invention.

Now referring to FIG. 4, MEMS device 100 is shown at a later stage of manufacture. Vias 141 are filled
10 with an electrically conductive material such as, for example, copper, gold, aluminum, alloys of copper, alloys of gold, and the like, to form conductively filled vias 140. It should be noted that a filled via does not need to be completely filled to be considered
15 a filled via. Rather, a filled via can be partially filled as long as electrical contact can be made from surface 111 to surface 112.

A conductive layer is patterned on surface 111 of packaging substrate 110 to form electrical
20 interconnects 127, 129, and 130, which are in electrical contact with corresponding conductively filled vias 140. Suitable materials for electrical interconnects 130 include aluminum, gold, copper, nickel, tin, alloys of aluminum, gold, copper, nickel
25 or tin, cobalt, chromium, silicides of tungsten or tantalum, filled epoxies, filled silicones, or the like. It should be understood that electrical interconnects 130 are an optional feature.

A conductive layer is patterned on surface 112 of
30 packaging substrate 110. This conductive layer forms the basis for several of the MEMS components 124 such as MEMS switches and MEMS sensors. By way of example, the conductive layer may be patterned to form control leads 121, transmission terminals 122, control

electrode 125, and travel stops 123. Control leads 121 are electrically coupled to corresponding electrical interconnects 130 by conductively filled vias 140. In this example, control leads 121 conduct the actuation voltage in the case of a MEMS switch, which switch may be formed from the conductive layer on surface 112. Transmission terminals 122 are RF input/output terminals. The thicknesses of each of the traces on surface 112, i.e., control leads 121, transmission terminals 122, control electrode 125, and travel stops 123 may be the same or different depending on the particular application. The thicknesses may be varied by, for example, altering the deposition of the material forming the conductive layer.

Additionally, a substrate trace 113 may be formed from the conductive layer patterned on surface 112. Substrate trace 113 is optional and is used for bonding a protective cap 150 to packaging substrate 110 as described with reference to FIG. 5. Further, substrate trace 113 can be manufactured from either electrically conductive or electrically nonconductive material. Suitable materials for electrical interconnects 113 include aluminum, gold, copper, nickel, tin, alloys of aluminum, gold, copper, nickel or tin, cobalt, chromium, silicides of tungsten or tantalum, nonelectrically conductive material suitable for bonding, or the like.

FIG. 5 is a cross-sectional side view of MEMS device 100 further along in manufacture. A center hinge 130 is coupled to substrate 110 via an anchor 131. Anchor 131 is typically a conductively filled via. Center hinge 130 is electrically connected to a control electrode 132. Control electrode 132 is electrically isolated from control electrode 125, but

electrically coupled to at least one of vias 140. By way of example, control electrode 132 is comprised of an electrically nonconductive material, i.e., a dielectric material 133 and an electrically conductive material 134. A suitable material for dielectric layer 133 is silicon oxide nitride. Preferably, layer 134 is comprised of a metal having minimum stiffness and a low thermal expansion coefficient such as, for example, copper, gold, or the like. The geometry of control electrode 132 may vary to optimize charge distribution. By way of example, center hinge 130 and control electrode 132 are formed from the same dielectric and metal layers. The particular materials for layers 133 and 134 are not a limitation of the present invention.

Control electrodes 125 and 132 form a cantilever structure, wherein control electrode 125 is referred to as a lower control electrode and control electrode 132 is referred to as an upper control electrode.

A shorting bar 135 is connected to control electrode 132 for shorting control leads 121 to transmission terminal 122. Thus, shorting bar 135 is positioned over control electrode 125 and transmission terminal 122. Because there is metal to metal contact between shorting bar 135 and transmission terminal 122, it is preferred that shorting bar 135 and transmission terminal 122 be made of different metals. The different metals should each possess a high melting point to reduce stiction and each should be resistant to oxidation to promote reliability.

A protective cap 150 having a cap bonding layer 151 at the bonding perimeter is placed over MEMS component 120 such that it mates with substrate trace

113. Preferably, the composition of substrate trace 113 and cap bonding layer 151 are chosen to achieve alloy bonding therebetween at a temperature less than that of other metals or components of MEMS device 100.

5 In accordance with the present invention, the alloy bonding can be achieved at temperatures ranging from approximately 200°C to 300°C and more preferably at temperatures ranging from approximately 200°C to 250°C. It should be understood that if a hermetic seal is not

10 desired, cap bonding layer 151 can be comprised of filled epoxies or filled silicones.

Now referring to FIG. 6, what is shown is a top view of MEMS device 100 in accordance with an embodiment of the present invention prior to sealing

15 with protective cap 150. FIG. 6 further illustrates substrate trace 113 having a rectangular geometry. It should be understood that the geometry of substrate trace 113 is such that it will coincide with cap bonding layer 151. Other suitable geometries for trace

20 113 and protective cap 150 which can perform substantially the same sealing or protective function include square, circular, pentagonal, and the like.

It should be further understood that trace 113 also forms a planar surface, i.e., a surface without

25 topological deviation, which enhances the formation of a hermetic seal with protective cap 150 is attached.

Packaging substrate 110 which has a plurality of hermetically sealed and packaged MEMS devices 100 is separated into individual devices for test and

30 shipment.

By now it should be appreciated that a MEMS device having a monolithic MEMS component integral with a substrate and a method for manufacturing the MEMS

device that are cost efficient and easily integrable into a manufacturing process have been provided. The assembly and packaging for MEMS devices in accordance with the present invention offers several advantages not available with prior art techniques. For example, the MEMS device is fabricated directly from the packaging substrate rather than as a separate component which has to be mounted to a packaging substrate. Incorporating vias and metal interconnects eliminates the need for wirebonds, thereby reducing the problems associated with parasitic inductances in RF applications. Moreover, the MEMS device of the present invention has a planar surface, which permits hermetically sealing the MEMS components 124 within a cavity. The elimination of wirebonds provides for the manufacture of a smaller MEMS device compared to MEMS devices having wirebonds. In addition, the present invention allows bonding the protective cap at temperatures lower than other processing temperatures, which reduces the probability of temperature damage to the MEMS device.

While specific embodiments of the present invention have been shown and described, further modifications and improvements will occur to those skilled in the art. It is understood that the invention is not limited to the particular forms shown and it is intended for the appended claims to cover all modifications which do not depart from the spirit and scope of this invention. For example, other embodiments could be fabricated to include one or more passive devices, i.e., capacitors, inductors, resistors, within packaging substrate 110 or between packaging substrate 110 and MEMS component 120. Such embodiments would include a more complicated network of

vias to interconnect the passive components with each other and with a MEMS component.

CLAIMS

1. A method for manufacturing a Micro-
5 Electromechanical Systems (MEMS) device, comprising:
providing a substrate (110) having first and
second major surfaces (111, 112);
fabricating a plurality of conductively filled
vias (141) extending from the first major surface to
10 the second major surface;
forming a MEMS component (124) integral with the
substrate; and
forming a first conductive layer over the first
major surface of the substrate, a first portion of the
15 first conductive layer electrically connected to a
first of the plurality of conductively filled vias.
2. The method of claim 1, further including
forming a substrate trace on the first major surface.
20
3. The method of claim 2, further including
coupling a protective cap to the substrate trace.
4. The method of claim 3, wherein bonding the
25 protective cap to the substrate trace includes forming
a hermetic seal.
5. The method of claim 3, wherein the protective
cap is made from an electrically conductive material.
30
6. The method of claim 1, further including
forming a travel stop of the first major surface.

7. The method of claim 1, further including forming an electrical interconnect on the second major surface, the electrical interconnect contacting the conductively filled via.

5

8. The method of claim 1, further including forming a second conductive layer over the second major surface, wherein a first portion of the second conductive layer is electrically connected to at least one of the conductively filled vias.

10


9. The MEMS device of claims 3, 4, or 5, wherein the protective cap comprises a base structure having a periphery, wherein walls extend from the periphery.

15


10. The MEMS device of claims 3, or 4, or 5, or 9, wherein a material of the protective cap bonding layer is selected from the group of material consisting of aluminum, gold, copper, nickel, tin, an alloy of aluminum, an alloy of gold, an alloy of copper, an alloy of nickel, an alloy of tin, cobalt, chromium, a silicide of tungsten, a silicide of tantalum, filled epoxies, and filled silicones.

20


25




- PRIOR ART - **FIG. 1** 10



- PRIOR ART - **FIG. 2** 20



100 **FIG. 3**



100 **FIG. 4**




FIG. 5




FIG. 6

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 August 2001 (09.08.2001)

PCT

(10) International Publication Number
WO 01/56920 A3

(51) International Patent Classification⁷: **B81B 7/00**
(21) International Application Number: **PCT/US01/03210**
(22) International Filing Date: 31 January 2001 (31.01.2001)
(25) Filing Language: English
(26) Publication Language: English
(30) Priority Data:
09/495,786 1 February 2000 (01.02.2000) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:


— with international search report

(88) Date of publication of the international search report:
14 February 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(71) Applicant: **MOTOROLA, INC.** [US/US]: 1303 East Algonquin Road, Schaumburg, IL 60196 (US).
(72) Inventors: **HUANG, Jenn-Hwa**; 1426 West Tara Drive, Gilbert, AZ 85233 (US). **COFFMAN, Samuel, L.**; 11603 North 86th, Scottsdale, AZ 85260 (US). **SUN, Xi-Quing**; 100 West Nopal Place, #236, Chandler, AZ 85225 (US). **XU, Ji-Hai**; 1232 South Buchanan Street, Gilbert, AZ 85233 (US). **PARSEY, John, Michael, Jr.**; 1321 East Desert Flower Lane, Phoenix, AZ 85048 (US).
(74) Agent: **KOCH, William, E.**; Motorola, Inc., Intellectual Property Dept., P.O. Box 10219, Scottsdale, AZ 85271-0219 (US).

(54) Title: MICRO-ELECTROMECHANICAL SYSTEM DEVICE



(57) Abstract: A Micro-Electromechanical Systems (MEMS) device (100) having conductively filled vias (141). A MEMS component (124) is formed on a substrate (110). The substrate has conductively filled vias (140) extending therethrough. The MEMS component (124) is electrically coupled to the conductively filled vias (140). The MEMS component (124) is covered by a protective cap (150). An electrical interconnect (130) is formed on a bottom surface of the substrate (110) for transmission of electrical signals to the MEMS component (124), rather than using wirebonds.



WO 01/56920 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/03210

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B81B7/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B81B H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, INSPEC, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|----------|--|-----------------------|
| X | EP 0 851 492 A (TEXAS INSTRUMENTS INC) 1 July 1998 (1998-07-01) figures 1,2 column 2, line 27 - line 38 column 3, line 20 -column 6, line 24 | 1-4,7-10 |
| Y | --- | 5 |
| A | --- | 6 |
| Y | EP 0 637 871 A (MATSUSHITA ELECTRIC IND CO LTD) 8 February 1995 (1995-02-08) figures 1-5 column 5, line 20 -column 8, line 57 | 5 |
| A | --- | 1-4,7-10 |
| | --- -/-- | |



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

26 October 2001

Date of mailing of the international search report

06/11/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Polesello, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/03210

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

| Category | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|----------|---|-----------------------|
| X | US 5 610 431 A (MARTIN JACOB H) 11 March 1997 (1997-03-11) figure 8 column 2, line 58 -column 3, line 19 column 7, line 35 -column 8, line 4 | 1-4,6-8 |
| A | ---- | 5,9,10 |
| X | US 5 511 428 A (GOLDBERG HOWARD D ET AL) 30 April 1996 (1996-04-30) figures 1-10 column 3, line 13 -column 6, line 10 column 7, line 22 -column 21, line 35 | 1,2,6-8 |
| A | ---- | 1-4,7-10 |
| A | FR 2 780 200 A (COMMISSARIAT ENERGIE ATOMIQUE) 24 December 1999 (1999-12-24) figures 1,5-8 page 2, line 4 - line 22 page 9, line 32 -page 14, line 9 | 1-5,10 |
| A | ---- | |
| A | US 5 668 033 A (KANAMORI KATUHIKO ET AL) 16 September 1997 (1997-09-16) figures 1-8,10-13,22-34 column 1, line 58 -column 2, line 32 column 3, line 33 -column 9, line 6 column 11, line 16 -column 13, line 12 ----- | |

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/03210

| Patent document cited in search report | | Publication date | Patent family member(s) | Publication date |
|---|---|---------------------|----------------------------|---------------------|
| EP 0851492 | A | 01-07-1998 | EP 0851492 A2 | 01-07-1998 |
| | | | JP 10189822 A | 21-07-1998 |
| EP 0637871 | A | 08-02-1995 | DE 69415235 D1 | 28-01-1999 |
| | | | DE 69415235 T2 | 20-05-1999 |
| | | | EP 0637871 A1 | 08-02-1995 |
| | | | JP 7099420 A | 11-04-1995 |
| | | | NO 942926 A | 07-02-1995 |
| | | | US 5459368 A | 17-10-1995 |
| US 5610431 | A | 11-03-1997 | NONE | |
| US 5511428 | A | 30-04-1996 | NONE | |
| FR 2780200 | A | 24-12-1999 | FR 2780200 A1 | 24-12-1999 |
| | | | EP 1090419 A1 | 11-04-2001 |
| | | | WO 9967818 A1 | 29-12-1999 |
| US 5668033 | A | 16-09-1997 | JP 8316497 A | 29-11-1996 |
| | | | DE 19619921 A1 | 05-12-1996 |